

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N. 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O. Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

CLIENT :

NSW LEATHER CO PTY LTD 707 ELIZABETH STREET

TEST NUMBER DATE

562843-MN 21/10/2008

WATERLOO NSW 2017

SAMPLE DESCRIPTION

Clients ref: "Sovereign"

Leather submitted Colour: Taupe

Approx thickness: 1.2 to 1.4mm

End use: Upholsterv

THESE RESULTS MUST BE CONSIDERED IN CONJUNCTION WITH THE COMMENTS ON THE FOLLOWING PAGE(S)

Material Specification provided by client:

Nominal composition: Leather

Approx. mass: 11785/m2

AS/NZS

1530.3 - 1999

Simultaneous determination of Ignitability, Flame

Propagation, Heat Release and Smoke Release

RESULTS:

Face tested: Face

Date tested: 20/10/2008

	Mean	_	Standard Err
Ignition time	4.89	min	0.26
Flame propagation time	Nil '	s	Nil
Heat release integral	113.7	kJ/m2	6.6
Smoke release, log d	-1.2180		0.1550
Optical density, d	0.0798	/m	1

Number of specimens ignited:

Number of specimens tested:

REGULATORY INDICES:

		1
Ignitability Index	15	Range 0-20
Spread of Flame Index	0	Range 0-10
Heat Evolved Index	4	Range 0-10
Smoke Developed Index	4	Range 0-10

171023

0204/11/06

ተለሰ 😘

٦

(CONTINUED NEXT PAGE)

PAGE

Augualian Wool Tosting Authority Ltd
Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Teating Authorities, Australia for Accreditation No.

- Chamical Tusting of Textiles & Related Products - Machanical Testing of Textiles & Helated Products

Accreditation No Accreditation No. 1356

- Heat & Temperature Measurement This document is issued in accordance with NATA's accreditation requirements. Samples, and their idsplifying descriptions have been provided by the client unless otherwise aloud AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tasted. This document shall not be reproduced except in full and shall be rendered void if amended or allered. This document the names AWTA Product) Teating and AWTA Ltd may be used in advertising providing the content and formal of the advertising providing the content and formal of the advertising providing the providing the content and formal of the advertising providing the content and the conten

Managing Director of AWTA Ltd.

andolal

สรินักสริ Sunfluien



Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N. 43 006 014 106

1st Floor, 191 Rececourse Road, Flemington, Victoria 3031 P.O. Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

NSW LEATHER CO PTY LTD CLIENT : 707 ELIZABETH STREET

WATERLOO NSW 2017

TEST NUMBER

: 7-562\$43-MN

DATE

: 21/10/2008

Comments:

These results only apply to the specimen mounted, as described in this report.

The results of this fire test may be used to directly assess fire hazard, but it should be recognized that a single test method will not provide a full assessment of fire hazard under all fire conditions.

The reaction of thin unsupported flexible materials to flame impingement can be assessed in accordance with AS 1530.2. Where materials of thickness less than 2mm that are sufficiently flexible to be bent by hand around a mandrel of 2mm diameter or less are subjected to the test described herein, they should. also be subjected to the test in AS 1530.2.

Each test specimen had an unattached backing of 4.5mm thick fibre reinforced cement board.

Each test specimen was restrained on the exposed face by a layer of galvanised welded square mesh made from wire of nominal diameter 0.8mm and nominal spacing 12mm in both directions and securely fixed to a backing boar; at four points each 100mm from the centre of the sample and the assembly clamped in four places.

To allow free movement of sample during testing all corners were folded away from the clamps.

171023

PAGE

© Australian Wool Tasting Authority Ltd Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for Accreditation No. 983 - Chemical Testing of Taxilles & Related Products - Machanical Tosting of Textiles & Related Products Accreditation No

- Haat & Temperature Messurement

Accreditation No. 1355

This document is issued in accordance with NATA's accreditation requirements. Samples, and their identifying descriptions have been provided by the client unless otherwise stated AWTA Ltd makes no warranty, implied or otherwise, as to the source of the lented camples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered word if amended or aftered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and formal of the advertisers and have been approved in advance by the Managing Director of AWTA Ltd andolal

APPROVED SIGNATORY

JANUALION B SUIT

0204/11/05