

Colour fastness to rubbing Dry 1000 cycles, Wet 500 cycles Perspiration (ISO 11641) 100 cycles, Evaluation ISO 105 A-03	ISO 11640	> = 4 > = 4 > = 4
Colour fastness to light Exposure Conditions N 3 (table 3) apparatus Type C (Atlas CI 3000+) Irradiance 1,2 W/m ² at 420 nm Exposure Method 3, 1 Exposure 80 hours (345 KJ/ m ² at 420 nm)	ISO 105 B-06	> = 6
Cold crack resistance of finish Temperature +30°C	ISO 17233	No Cracks
Finish Adhesion Dry Adhesion Wet Adhesion	ISO 11644	> = 5 N/Cm > = 3 N/Cm
Burning Behaviour	ISO 3795	< = 75 mm/min
Flexing Endurance 100,000 Cycles	ISO 5402	No Cracks
Tear Strength	ISO 3377-1	> = 30 N
Fogging Test Gravimetric Method, point 8.5.3	ISO 6452	< = 5 mg
Migration Staining	ISO 15701	> = 4
Tensile Strength and Elongation	ISO 3376	> = 12 N/mm ² 35 - 60%
Colour fastness to water spotting	ISO 15700	OK
Abrasion 2000 cycles, Wheels CS 10, Load 500 g	ISO 5470	No Cracks
Artificial Ageing 168 hours, 38°C 98% RH 168 hours, 93°C		> = 4/5 > = 4/5
Dry Heat Shrinkage 168 hours, 93°C		< = 5%