

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : NSW Leather Co Pty Ltd
16 Anderson Street
Banksmeadow NSW 2019

Test Number : 16-000851
Issue Date : 02/03/2016
Print Date : 3/03/2016

Sample Description Clients Ref : "LAGUNA"
Leather Swatches
Colour : Brown
End Use : Furniture, Wall Panels etc
Nominal Composition : Leather Cowhide Bovine
Nominal Mass per Unit Area/Density : Approx. 560g/m²
Nominal Thickness : 0.9-1.1mm

ISO 5660.1-2015

Reaction to Fire Tests - Heat Release Smoke Production and Mass Loss Rate Part 1: Heat Release Rate (Cone Calorimeter Method) and Smoke Production Rate (Dynamic Measurement)

	Specimen			Mean	
	1	2	3		
Average Heat Release Rate	10.3	12.1	10.5	11.0	kW/m ²
Group Number Classification	1S	1S	1S		

(In Accordance with New Zealand Building Code Verification Method C/VM2 Appendix A)

Average Specific extinction area	36.7	20.3	28.7	28.6	m ² /kg
----------------------------------	------	------	------	------	--------------------

Test orientation : Horizontal

	Specimen			Mean	
	1	2	3		
Irradiance	50	50	50	50	kW/m ²
Exhaust flow rate	24	24	24	24	L/sec
Time to sustained flaming	19	23	20	21	sec
Test duration	1819	1823	1820	1821	sec

30203

10449

Page 1 of 8

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for :
- Chemical Testing of Textiles & Related Products : Accreditation No. 983
- Mechanical Testing of Textiles & Related Products : Accreditation No. 985
- Heat & Temperature Measurement : Accreditation No. 1356

This document is issued in accordance with NATA's accreditation requirements. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the




APPROVED SIGNATORY


MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : NSW Leather Co Pty Ltd
16 Anderson Street
Banksmeadow NSW 2019

Test Number : 16-000851
Issue Date : 02/03/2016
Print Date : 3/03/2016

Peak heat release after ignition	69.4	77.2	91.6	79.4	kW/m ²
Average heat at 60 s	57.0	63.0	66.0	62.0	kW/m ²
Average heat at 180 s	42.4	47.9	50.5	46.9	kW/m ²
Average heat at 300 s	33.4	36.6	37.1	35.7	kW/m ²
Total heat released	18.5	21.8	19.0	19.8	MJ/m ²
Average effective heat of combustion	8.1	9.3	7.7	8.3	MJ/kg
Initial thickness	7.1	7.1	7.1	7.1	mm
Initial mass	86.8	87.1	88.9	87.6	g
Mass remaining	67.9	67.6	68.6	68.0	g
Mass percentage pyrolysed	21.8	22.4	22.8	22.3	%
Mass loss	18.9	19.5	20.3	19.6	g
Average rate of mass loss	1.3	1.3	1.4	1.3	g/m ² .s

These test results relate only to the behaviour of the product under the conditions of the test, they are not intended to be the sole criterion for assessment of performance under real fire conditions.

Samples were loose laid onto a substrate of 6mm thick cement sheeting prior to testing.

Tests were conducted with a wire grid placed over the sample during testing. This was done to contain intumescent sample within the sample holder.

Note: All calculations are based on ignition + 30 minutes.

30203

10449

Page 2 of 8

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for :
- Chemical Testing of Textiles & Related Products : Accreditation No. 983
- Mechanical Testing of Textiles & Related Products : Accreditation No. 985
- Heat & Temperature Measurement : Accreditation No. 1356

This document is issued in accordance with NATA's accreditation requirements. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the



APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

0204/11/06

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499


TEST REPORT

Client : NSW Leather Co Pty Ltd
16 Anderson Street
Banksmeadow NSW 2019


Test Number : 16-000851
Issue Date : 02/03/2016
Print Date : 3/03/2016

Specimen : 1


Heat release rate (kW/m²)




Effective heat of combustion (MJ/kg)



Smoke production rate ([m²/s])



Specific extinction area (m²/kg)



30203

10449

Page 3 of 8

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for :

- Chemical Testing of Textiles & Related Products	: Accreditation No.	983
- Mechanical Testing of Textiles & Related Products	: Accreditation No.	985
- Heat & Temperature Measurement	: Accreditation No.	1356

This document is issued in accordance with NATA's accreditation requirements. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the



APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051


Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT


Client : NSW Leather Co Pty Ltd
16 Anderson Street
Banksmeadow NSW 2019

Test Number : 16-000851
Issue Date : 02/03/2016
Print Date : 3/03/2016


Mass loss rate (g/s)




Total heat released (MJ/m²)



Mass (g)



Rate of smoke release (l/m²/s/m²)



30203

10449

Page 4 of 8

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for :

- Chemical Testing of Textiles & Related Products	:	Accreditation No.	983
- Mechanical Testing of Textiles & Related Products	:	Accreditation No.	985
- Heat & Temperature Measurement	:	Accreditation No.	1356

This document is issued in accordance with NATA's accreditation requirements. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the



APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499


TEST REPORT

Client : NSW Leather Co Pty Ltd
16 Anderson Street
Banksmeadow NSW 2019


Test Number : 16-000851
Issue Date : 02/03/2016
Print Date : 3/03/2016

Specimen : 2


Heat release rate (kW/m²)




Effective heat of combustion (MJ/kg)



Smoke production rate ([m²/s])



Specific extinction area (m²/kg)



30203

10449

Page 5 of 8

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for :

- Chemical Testing of Textiles & Related Products	: Accreditation No.	983
- Mechanical Testing of Textiles & Related Products	: Accreditation No.	985
- Heat & Temperature Measurement	: Accreditation No.	1356

This document is issued in accordance with NATA's accreditation requirements. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the



AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051


Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT


Client : NSW Leather Co Pty Ltd
16 Anderson Street
Banksmeadow NSW 2019

Test Number : 16-000851
Issue Date : 02/03/2016
Print Date : 3/03/2016


Mass loss rate (g/s)




Total heat released (MJ/m²)



Mass (g)



Rate of smoke release (l/m²/s/m²)



30203

10449

Page 6 of 8

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for :

- Chemical Testing of Textiles & Related Products	:	Accreditation No.	983
- Mechanical Testing of Textiles & Related Products	:	Accreditation No.	985
- Heat & Temperature Measurement	:	Accreditation No.	1356

This document is issued in accordance with NATA's accreditation requirements. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the



APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499


TEST REPORT

Client : NSW Leather Co Pty Ltd
16 Anderson Street
Banksmeadow NSW 2019


Test Number : 16-000851
Issue Date : 02/03/2016
Print Date : 3/03/2016

Specimen : 3


Heat release rate (kW/m²)




Effective heat of combustion (MJ/kg)



Smoke production rate ([m²/s])



Specific extinction area (m²/kg)



30203

10449

Page 7 of 8

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for :

- Chemical Testing of Textiles & Related Products	: Accreditation No.	983
- Mechanical Testing of Textiles & Related Products	: Accreditation No.	985
- Heat & Temperature Measurement	: Accreditation No.	1356

This document is issued in accordance with NATA's accreditation requirements. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the

APPROVED SIGNATORY



MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051


Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT


Client : NSW Leather Co Pty Ltd
16 Anderson Street
Banksmeadow NSW 2019

Test Number : 16-000851
Issue Date : 02/03/2016
Print Date : 3/03/2016


Mass loss rate (g/s)




Total heat released (MJ/m²)



Mass (g)



Rate of smoke release (l/m²/s)/m²)



30203

10449

Page 8 of 8

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for :

- Chemical Testing of Textiles & Related Products	:	Accreditation No.	983
- Mechanical Testing of Textiles & Related Products	:	Accreditation No.	985
- Heat & Temperature Measurement	:	Accreditation No.	1356

This document is issued in accordance with NATA's accreditation requirements. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the



APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR